# BOYSEN® WALLGUARD

**Dirt Resisting Exterior Latex Paint** 





For technical reasons connected with color reproduction and paint manufacturing, the colors shown may not match the exact paint color

# BOYSEN® WALLGUARD™

# **Dirt Resisting Exterior Latex Paint**

Introducing a new breed of latex paint that has a very high resistance to dirt, dust, smog and mildew. It can be painted even in a rigorous environment where there is a very high concentration of airborne pollutants.

- ✓ 100% Acrylic
- ✓ Highly resistant to airborne pollutants and dust
- ✓ Highly alkaline resistant
- ✓ Resists fading, cracking, and peeling
- ✓ Good exterior durability
- ✓ Excellent gloss retention
- ✓ Mildew resistant
- ✓ Good block and scrub resistance

# SURFACE PREPARATION

#### **New Concrete**

Allow new concrete to dry 14-28 days under normal weather conditions before painting. Surface to be painted should be clean and dry, free from oil, grease, dust, dirt, contaminants, and all loose grit and mortar. If neutralizing, treat surface with a solution of 1 part BOYSEN Masonry Neutralizer B-44 diluted in 16 parts water, applying liberally by brush or roller. Let dry before painting. However, if the concrete has been cured for more than 28 days, there is no need for neutralizer.

# Repainting

Scrape off all loose, scaling, flaking, and peeling paint manually or by using BOYSEN Paint and Varnish Remover B-141, as necessary. Wash surfaces clean and completely remove chemical residue. Let it dry.

For repainting concrete with chalky old paint, use BOYSEN Chalk Blocker B-7304 as surface conditioner. In case of mildew infestation, treat with a bleach solution (1:3, laundry bleach to water, respectively) by swabbing or brushing. To ensure proper treatment, let stand for 24 hours before cleaning off residue. Let dry.

For technical reasons connected with color reproduction and paint manufacturing, the colors shown may not match the exact paint color

#### **TECHNICAL DATA**

# **Principal Uses**

Use Boysen Wallguard B-5715 as an exterior finish for newly constructed buildings as well as repainting old structures

# **Practical Coverage**

30-35 square meters/gal./coat

# **Dry Time**

Touch dry in 1 hour. Recoat in 2 hours

# **Thinning**

Use as supplied (If necessary, thin with not more than 1/2 Liter of clean water per 4-Liter can)

# **Application**

Paint brush, roller or airless spray

# **Packaging**

4-Liter and 16-Liter cans

#### **Finish**

Semi-Gloss

# **Tinting**

Will accept BOYSEN Latex Colors at a maximum level of 1/4 Liter per 4-Liter can

Take note that B-1466 Hansa Yellow and B-1407 Toluidine Red are not recommended for Wallquard

### **PAINTING SCHEDULE**

# New Painting

#### Primer

BOYSEN® Acrytex™ Primer B-1705

#### **Putty**

BOYSEN® Acrytex™ Cast B-1711

# **Topcoat**

BOYSEN® Wallguard™ B-5715 (2 coats)

# Repainting

# **Topcoat**

Apply two coats of BOYSEN® Wallguard™ B-5715 on properly prepared surface

# SUGGESTED COLORS



<sup>\*</sup>Due to technical reasons connected with ink-printing and color reproduction, swatches shown here may differ from the exact paint color. Always refer to actual paint color standards to confirm your color.



# PACIFIC PAINT (BOYSEN) PHILIPPINES, INC.







B Blog: myboysen.com
B studioboysen.com











For technical reasons connected with color reproduction and paint manufacturing, the colors shown may not match the exact paint color